Lib.

FACTORS AFFECTING ROTOR SPINNING
OF FINE COTTON YARNS

by

AHMED SAYED SOLIMAN, B.S., M.S.

A DISSERTATION

IN

AGRICULTURE

Submitted to the Graduate Faculty
of Texas Tech University in
Partial Fulfillment of
the Requirements for
the Degree of

DOCTOR OF PHILOSOPHY

Approved

Accepted

August, 1985

AC
801
T3
1985
No. 63
c.p. 22

ACKNOWLEDGMENTS

I am deeply indebted to Dr. Jack Gipson (Plant and Soil Science Department) and Dr. Robert Steadman (Textile Research Center) for their direction of this research and their valuable guidance; and to the other members of my committee, Dr. Norman Hopper, Dr. R. D. Mehta, and Mr. James S. Parker, Director of the Textile Research Center, Lubbock, Texas, for their helpful criticism.

I also wish to thank all the staff of the Textile Research Center, especially Mr. Bill Cole; and Computer Services, particularly Mr. Dennis Edwards, for making this study more beneficial and enjoyable.

TABLE OF CONTENTS

ACKNOWLEDGMENTS	ii
LIST OF TABLES	iv
I. INTRODUCTION	1
II. REVIEW OF LITERATURE	3
III. MATERIALS AND METHODS	18
IV. RESULTS	25
V. DISCUSSION	36
VI. CONCLUSIONS	52
REFERENCES	55
APPENDIX	63

LIST OF TABLES

1.	EXAMINED FACTORS AND THEIR LEVELS	22
2.	EFFECT OF COMBING ON FIBER PROPERTIES OF COTTON SLIVERS	26
3.	COTTON YARN APPEARANCE	28
4.	YARN END-BREAKAGE RATE PER ROTOR HOUR	29
5.	YARN EVENNESS (C.V.%)	31
6.	YARN TENACITY (g/tex)	32
7.	SUMMARY OF ANALYSES OF VARIANCE	33
8.	SUMMARY OF MAIN EFFECTS	34
9.	YARN APPEARANCE: PREPARATION X SLIVER WEIGHT X COUNT INTERACTION	37
10.	YARN APPEARANCE: FIBER X SLIVER X COUNT INTERACTION	38
11.	END-BREAKAGE RATE: FIBER X COUNT X TWIST INTERACTION	40
12.	END-BREAKAGE RATE: FIBER X PREPARATION X SLIVER INTERACTION	41
13.	EVENNESS: SLIVER X COUNT X TWIST INTERACTION	43
14.	EVENNESS: PREPARATION X TWIST INTERACTION	43
15.	EVENNESS: PREPARATION X SLIVER INTERACTION	44
16.	EVENNESS: FIBER X TWIST INTERACTION	45
17.	EVENNESS: FIBER X COUNT INTERACTION	46
18.	EVENNESS: FIBER X SLIVER INTERACTION	47
19.	TENACITY: FIBER X PREPARATION X SLIVER INTERACTION	48
20.	TENACITY: FIBER X TWIST INTERACTION	50

CHAPTER I

INTRODUCTION

Commercial rotor spinning began in 1967 in Czechoslovakia. Since that time, many researchers have studied factors that affect rotor spinning of fine yarns. At the present, the break-even point, i.e., the economical count beyond which rotor spinning becomes more expensive than conventional ring spinning, is becoming ever finer, and is now approaching Ne 30 (the English system is used for yarn count). The alternative count system, tex or gram/kilometer, is given by $\text{tex} \times \text{Ne} = 590.6$.

The purpose of this research was to study the interaction between five principal factors known to influence rotor spinning of fine cotton yarns. The factors investigated were raw material, preparation, sliver weight, count, and twist. The study was set up as a factorial design with two replications.

The general effect of varying any one of these factors on rotor spinning is already well understood. By examining their interactions, however, it was deemed possible to acquire information on a number of other troublesome questions which are enumerated as follows:

1. Is combing beneficial generally, or only at fine counts, or only with long-staple cottons?
2. Is a long-staple cotton generally advantageous, or only at low twist?

3. When a low-micronaire cotton is used, under what conditions, if any, does the higher number of fibers in the yarn cross-section offset the tendency to form neps? Is the net effect of a fine cotton a function of yarn count?
4. To what extent is very high draft undesirable, i.e., should finer slivers be used in spinning fine yarns?
5. Are there high-order interactions, e.g., does fine yarn call for a long combed fiber with a low sliver weight?
6. Are the results of spinning performance consistent with those obtained by measuring yarn properties such as evenness, tenacity and appearance?

CHAPTER II

REVIEW OF THE LITERATURE

2.1. The History of Spinning

Seven thousand years ago spinning was already well established as a domestic craft. At that time and until the early middle ages spinning was an incredibly slow and tedious task. Throughout this period the spinning of one pound of cotton into a yarn suitable for the weaving of what we would now regard as a fairly heavy apparel fabric would keep a spinner busy for several weeks.

The earliest spinners probably twisted the yarn directly between finger and thumb but the spindle-and-whorl (a small clay, stone or hardwood flywheel to facilitate rapid rotation of the spindle) became the universal tool of spinners at an early date. The process was necessarily discontinuous.

With the wheel-driven spindle, as with the simple spindle, spinning remained a discontinuous process, and it was not until 1519 that Leonardo da Vinci invented a continuous spinning device, the spindle-and-flyer mechanism. The invention of the flyer marked a big step forward in that, for the first time, it allowed twisting and winding-on to proceed simultaneously. An early embodiment of the principle, the Saxony wheel, appeared in 1555 and quickly became established as offering the most efficient way of spinning

the relatively coarse woolen yarns which were in great demand in Northern Europe.

In the 1760's, Richard Arkwright succeeded in establishing the first successful commercial mills, based on the use of the automatic continuous spinning machine, later known as the water frame.

The third and final step in this first phase of mechanization of spinning was the mule invented by Samuel Crompton in 1779, so-called because the mule was a hybrid between the roller drafting of the water frame (to achieve fineness) and the inherently stable system of drafting against running twist of the jenny. By this means it was found possible to spin yarns fine enough for the weaving of Indian-type muslins. The mule, too, was commercially successful, particularly for the spinning of fine yarns.

The opening years of the 19th century were years of frenzied activity. By this time the mule had become by far the most popular spinning machine. Eventually a completely automatic mule was devised by Richard Roberts, 1827.

In the same year (1828) that the cap frame appeared, John Thorp patented his ring frame. Only one year later the last important step was taken when Addison and Stevens patented the ring-and-traveler, a concept which became the dominant spinning device in the 20th century.

Jenny, mule, throstle, and ring frames introduced twist into the yarn being spun by rotating the package (or "bobbin") of yarn.

By 1960, there were many contenders for the great prize of introducing a commercially successful "open-end" spinning machine (Catling, 1983). The first development of a mill-scale open-end machine (Czech KS 200 Break Spinner) was demonstrated in 1966 by Vyzkumny Ustav Bavlnarsky (V.U.B.), a Textile Research Institute in Czechoslovakia. This machine was soon accepted in industry.

In 1967, the BD 200 rotor spinning machine--a modification of the previously mentioned machine--was also announced by the V.U.B.

Since that time, many workers have been interested in studying, applying, and developing rotor spinning machines.

2.2. Factors Affecting Rotor Spinning of Fine Cotton Yarns

Many factors are known to affect the process of rotor spinning; a number of these factors are as follows.

2.2.1. Raw Materials and Their Properties

The open-end rotor-spinning system is especially suitable for short-staple fibers (Lünenschloss et al, 1975). Good results were obtained by Vaughn and Rhodes (1977) using fiber of medium length, with intensive gin cleaning. Because trash accumulation in rotors makes this type of spinning especially sensitive to impurities, it was early realized that thorough cleaning is required (Lünenschloss and Hummel, 1968). Their conclusions were based on comparative trials in which American cotton was spun by both ring and rotor (BD 200)

systems. They showed that, despite the need for higher twist, the rotor yarn was better in most respects, such as evenness, abrasion resistance, extensibility and reduced hairiness, but the ring-spun yarn was stronger. A similar comparison using African cottons (Bruggeman, 1979) concluded that the method of spinning affects fabric properties in the warp and filling directions as much as do the origin and type of cotton.

Cheaper mechanically harvested cottons were rotor-spun on a BD 200 RC, a modified BD 200 machine equipped with a cleaning system (Pospisil, 1976). The yarns obtained had reduced breakage rate, and improved yarn quality, i.e., fewer thin and thick places. Using a PR-150-1 rotor spinning machine to make 250-tex cotton yarns, Shcherbakova et al (1983) likewise showed that lower-grade cotton can be processed on this machine, leading to fewer faults and a more regular yarn than those processed on the ring frame. Similar results were obtained by Chemie and Kowalski (1983) in mill trials on low-grade R3 Soviet cotton.

Several cottons of staple length $\leq 7/8$ " were spun in both ring and rotor machines (Pillay, 1975). He found that fabrics from O-E yarns had significantly lower breaking strength, tearing strength, and bursting strength than fabrics from ring-spun yarns; fabric breaking elongation, air permeability, and abrasion resistance were not substantially altered. Despite the fiber disorientation in rotor yarns, which prevents fibers from making their full potential contribution

to yarn strength, researchers at Texas Tech University (1978) reported that strong open-end spun yarn was produced from Paymaster 266 cotton. A 59-tex (Ne 10) yarn was found to have Uster single yarn strength of approximately 800 g.

The finest yarn count that could be spun in a Rieter M1/1 machine was found to be limited by the quality of the raw material, particularly fiber fineness (Stalder, 1979).

2.2.2. Preparation for Spinning

Despite improvements in trash extraction in rotor frames, it has long been known (e.g., Kluka and Wojciechowski, 1973) that thorough cleaning in preparatory processes is repaid by a reduced rate of end breakage during rotor spinning. Using Texas cotton, Towery (1976) found that 3 cardings and 2 drawings gave the best yarn strength by reducing plant residues and very short fibers before spinning. Simpson (1978) reported that strength of the O-E yarns from double-carded sliver is greater than from single-carded sliver.

The use of Crosrol web cleaners at the card, and card autolevelers, were examined by Vila et al (1982). Auto-leveling at the card increased the tenacity and breaking elongation of yarns spun in a BD 200 rotor frame, but only the elongation of yarns from a Süssen machine, however, conventional two-stage drawing improved yarn evenness and reduced the incidence of slubs and other imperfections. The sequence recommended by Borzunov and Puzanova (1978), who used a BD 200-M-69 machine is: tandem carding with a web

crusher and drawing zone, followed by a single drawing.

Uniform card sliver is necessary to produce strong yarn (e.g., Pützscher, 1976). Nep formation in carding was found to be lower in Indian Sujata and Hybrid 4 cottons when compared with two imported varieties (Giza 45 and Sudan XG2VS). When the fibers were combed, however, the imported cottons produced stronger and more even yarn.

Several other investigators have examined the effect of combing on rotor spinning, mostly using long-staple cotton. Artzt and Hehl (1978) made a comparative study of ring- and rotor-spun yarns from combed and carded sliver. The effects of sliver fineness, fiber strength, and combing on the properties of the yarns were all evaluated. Results suggested that quality criteria which necessitate combing for ring-spun yarns do not apply to rotor-spun yarns, and that the quality of rotor-spun yarns is not adversely affected by a certain proportion of short fibers. Knitted fabrics made from carded rotor yarn were comparable in most properties with those made from combed ring yarn, except that the hand of the rotor yarn was subjectively judged as being harsher (Bruno, 1980). Gupte et al (1981), studying four Indian cottons on a Platt Hartford comber, showed that all the important fiber length parameters such as mean fiber length, short fiber percentage, and dispersion percentage can together explain almost all the variations taking place in yarn strength after combing.

2.2.3. Sliver Weight and Spinning Draft

Open-end methods have the general advantage of allowing very high draft and enabling yarn to be spun direct from sliver. Drafts in the opening zone of about 100 are considered optimal for a BD 200 S machine (Audivert and Castellar, 1981). Drafts exceeding 300 are feasible as long as the delivery speed from the drafting system is high enough (Krause and Soliman, 1970). With a yarn withdrawal speed of 120 m/min they processed 4 kilotex sliver with a draft of 363. This maximum feasible draft is reduced at shorter staple lengths (Frey, 1974). As an example, Starodubov (1981), studying yarn formation during mass piecing-up on BD 200-M-69 machines, concluded that 18.5 and 50 tex (Ne 32 and 12) cotton yarns could be produced from a 3.7 ktex (52 gr/yd) sliver with a fiber length of 30 to 31 mm.

Very high draft causes uneven yarn and excessive end breaks. Finer sliver is recommended in spinning fine yarns (Landwehrkamp, 1979). For a yarn count of 33 to 100 tex (Ne 6 to 18) a sliver weight of about 4 ktex (56 gr/yd) is needed; for yarns of 25-33 tex (Ne 18 to 24) a sliver weight of 3.4 ktex (48 gr/yd) and for finer yarns of 20-25 tex (Ne 18 to 30), a sliver weight of 2.5-3 ktex (35 to 42 gr/yd) is recommended in order to avoid excessive drafts. Likewise, a formula for predicting yarn evenness developed by Seshan et al (1979) shows opening-roll draft as one of the three chief components of yarn irregularity.

2.2.4. Yarn Count Range

Rotor spinning has been more successful in spinning coarse yarns. As yarn becomes finer, ring spinning is generally more economic because spindle speed can be increased and the capital cost/spinning position is much lower. Knitting yarns in the range 12 to 400 tex were rotor-spun at the Textile Research Center, Lubbock, Texas (Towery, 1976). Rohlena (1977) reported that the BD system can produce yarn of fine counts. Tex counts of 15 and 17 were spun from medium-quality cottons. He added that the BD 200 S is a more universal machine able to spin yarns from 15 to 100 tex (Ne 6 to 40) with yarn-withdrawal speeds up to 150 m/min. The superior evenness of rotor yarns was found to extend to yarns as fine as 19 tex (Ne 31) spun on a BD 200 S machine (Lennox-Kerr, 1979). Attempts to spin finer yarns on rotor machines have met with excessive end-breakage rates. For example, workers at Texas Tech University (1980) spun 7 tex (Ne 80) yarn from grade 3 combed Pima cotton on Elitex BD 200 S at 10 rotor positions, but with 19 ends down/1.5 rotor hours. However, Sultan and El-Hawary (1974) found that the BD 200 open-end spinning machine could not be recommended for spinning fine yarns from long-staple Egyptian cotton. Instead, shorter cottons can be used more effectively to produce yarns of coarser count.

As distinct from technological possibility, economic feasibility has generally been limited to coarse and medium

counts (Stalder, 1972). Earlier, S.A.C.M. (1967), in marketing the Integrator which is a turbine spinning machine, advised that the effective range of yarn count is from 36 to 170 tex. Cizek (1968), using the BD 200 break spinning machine under mill conditions in Czechoslovakia, reported that the count range limits tested are from 15 to 62 tex (Ne 10 to 40) on fiber with staple length up to 40 mm. Similar conclusions were reached by Wassef (1972). Frey (1974) and Herold (1976) suggested an economic limit of 25 tex (Ne 24) and Lennox-Kerr (1974), referring to Platt Rotospin 833 and 835 machines, indicated 20 tex (Ne 30). Jain and Marwaha (1975) confirmed that the rate of return on investment in rotor spinning in the initial years is satisfactorily high for counts between 32 and 59 tex (Ne 10 and 18) and that, even for counts as fine as 20 tex, the long-term return is good. In general, it was considered profitable to adopt open-end spinning in India, particularly for mills producing coarse and medium counts. Commercial production by Daiwa was limited to yarns of 32 tex (Ne 18) and coarser (Konishi, 1976). A practical limit of 30 tex (Ne 20) was also found for blends of cotton and man-made fiber having staple lengths up to 40 mm (Tyukov et al, 1981).

Nikolic (1980) reported that the quantitative and economic indices for a 20 to 50 tex (Ne 12 to 30) yarn are significantly better if open-end spinning is used. However, the qualitative index is better and the range of application is

wider if ring spinning is used. Brunk (1982) used combed long-staple cotton to spin fine yarns in a rotor spinner. Starting with fiber counts of 100 mtex, it was possible to spin yarns of 14 to 16 tex (Ne 37 to 42). The study showed that the yarn strength efficiency is related to twist in a similar way for 110 to 170 mtex fiber. Cost analysis showed that rotor spinning of fine fibers into fine yarns is advantageous only in comparison with ring spinning of combed cotton.

Fine (21 tex = Ne 28) rotor yarn was found to be weaker and less rigid than ring-spun yarn. Coarser (49 to 67 tex or Ne 9 to 12) rotor yarns were more rigid than corresponding ring yarns (Tiranov et al, 1977).

Artzt and Schenek (1977) investigated the effect of rotor diameter, yarn count, and rotor speed on the minimum twist level. Rotors having diameters of 45, 55, and 65 mm over a yarn count range of between 25 and 125 tex (Ne 4 and 24) with rotor speeds from 45,000 to 65,000 rev/min, were used. Results showed that fine yarns should be spun on small rotors, while larger rotors were suitable for coarse yarns.

2.2.5. Yarn Twist

Cotton yarns spun on BD 200 spinning machines need 10-15% more twist than ring-spun yarns (Barella and Vigo, 1970; Herold, 1976). Audivert (1981) found that the more flattened twist/strength curves of rotor-spun yarns, compared with those of ring-spun yarns, were attributed to the increase in

fiber breakage and reduction of fiber straightening. Barella et al (1982) indicated that the diameter of cotton rotor yarns was influenced to a lesser extent by twist angle than ring yarns. Rotor-spun yarn was found to have a greater diameter than a conventional ring-spun yarn because of the different method of applying twist (Barella et al, 1984).

Higher twist values were found to be one answer to the problems of higher end-breakage rate and reduction of yarn breaking strength that characterize rotor spinning when compared with ring spinning, (Coll-Tortosa and Phoa, 1976). Audivert (1980) indicated that in rotor-spun cotton yarn, elastic recovery varied directly with yarn twist and inversely with percentage elongation. The effect of twist and draft on cotton yarn properties was studied by Polyakova (1980). She confirmed that twist should increase with indirect count by an exponent just above 0.5. Mitova (1981) found that the abrasion resistance increased with twist due to greater cohesion.

The resistance to repeated extensions of cotton rotor-spun yarns tends to increase as the twist increases (Barella and Manich, 1981). Researchers at Texas Tech University (1981) studied the influence of twist multiplier level on count-strength product. They found that yarns formed by a Platt T 883 spinning machine were superior to those formed by the older type of spinning unit. For combed long-staple fibers in the range 0.11 to 0.17 tex, the fiber-strength

utilization in yarns spun in a BD 200 RS machine increased directly with twist (Brunk, 1982). Barella et al (1983) concluded that twist did not affect yarn regularity, but it did influence very significantly the accumulated trash in the rotor. The most satisfactory twist was found to be 1200 t/m at yarn count of 16.5 tex (Ne 36) and twist multiplier of 4900, (Yurkova et al, 1983). The difference between the theoretical and the measured twist in rotor spun yarns was found to be affected by the type of rotor, the atmospheric pressure in the cleaning system, the rotational speed of the opening roller, and the number of fibers in yarn cross-section (Manich and Barella, 1984).

2.3. Yarn Properties

2.3.1. Yarn Appearance

The yarn produced by the rotor spinning method was characterized by a very even appearance and low breaking strength (Shimizu et al, 1968). Louis (1978), comparing the ASTM method and Uster evenness Tester data, indicated that the Uster data were found to be adequate in indicating grades, provided that a narrow range of yarn count was involved in each evaluation.

2.3.2. End Breakage in Spinning

In order to ensure normal operation of a BD 200 spinning machine, yarn breaks must not exceed 50/1,000 rotor

hours (Feigenberg et al, 1970). It is possible to reduce yarn breakages while at the same time reducing the amount of twist necessary for spinning on BD machines by fitting a guide edge of specified radius in the yarn withdrawal path (Hom, 1974). El-Messiry (1977) indicated that economic effectiveness in spinning Egyptian cotton was found to fall rapidly at a breakage rate exceeding 500 ends/1,000 rotor hours. Yarns with a linear density of 29.4 tex (Ne 20) were spun on PPM rotor spinning machines at rotor speeds of 60,000 r.p.m. with 40 breakages/1,000 rotor hours (Avrorov and Privalov, 1983).

2.3.3. Yarn Evenness

Krause and Soliman (1971), Douglas (1972), and Lord (1974) have stated that evenness of rotor-spun yarn was better than ring-spun yarn, due to the deposition of fibers on the inner wall of the spinning rotor. The effect of cotton fiber maturity on the irregularities of yarns spun on ring frames and rotor spinning machines was studied by Czaplicki (1973). He found that yarns spun on a ring frame from fully mature fibers were more regular than those from immature ones, while quality of rotor yarns was little affected by fiber maturity.

Because of the low number of thick places and knots after cleaning in coarse to medium counts, rotor-spun yarns have been considered ready for further processing without

winding (Rohlena, 1974). Delerm (1976) explained how the quality advantages of rotor-spun yarns (uniformity, absence of knots, good covering power) can be exploited.

2.3.4. Yarn Tenacity

Fibers migrate in spinning differently from those in ring-spun yarn and the fiber-helix wavelengths vary according to yarn radius; fiber tensions are lower. Bridging fibers are converted into hooks, thus reducing the effective fiber length in the yarn (Lord, 1971). These factors contribute to the weakness, bulk and extensibility of rotor yarns. Yarn strength increases as the fiber's staple length increases in the range 31.5 to 37.6 mm and its linear density decreases, but fiber strength utilization in the yarn decreases as staple length increases (Chukaev and Manakova, 1972). They concluded that fibers with shorter staple lengths were used more effectively in spinning on the BD 200 machine. Yarn strength was found to depend less on sliver uniformity than on the blending and cleaning derived from the two drawing processes that gave maximum yarn strength (Texas Tech University, 1978a). The lower yarn strength of rotor yarns from a BD 200 machine was explained by a decrease in modal length of 3 to 5 mm (Kochetkova and Kovacheva, 1976). Part of the low fiber-strength utilization in rotor yarns is explained by surface wrapper fibers, which comprise an increasing proportion of the yarn as yarn count becomes finer (Lünenschloss and Kampen, 1976). The effect of three types of rotor profiles (narrow-, medium-

and wide-grooved) in a Platt Saco-Lowell T 833 machine was examined (Texas Tech University, 1984a). The narrow groove produced the strongest and most uniform yarn.

The relationship between fiber and yarn properties has been described in a series of publications from the Textile Research Center. For a nearly constant micronaire value, 96% of rotor yarn strength variation at both 23 and 59 tex (Ne 10 and 26) can be explained by fiber strength variation (Texas Tech University, 1978b). The Stelometer instrument was found to be the most sensitive predictor of yarn strength (Texas Tech University, 1984b). Tests on Acala 1517-75 cotton and a hybrid Upland X Pima cotton on a Rieter M1/1 machine and a Saco-Lowell SF3H ring frame showed that the higher length and strength of the hybrid cotton contributed to high yarn strength regardless of yarn count (Texas Tech University, 1980).

2.4. General Comparison of Ring and Rotor Yarns

Many investigators, such as Locher and Kasperek (1967), Kasperek (1968), Barella and Torn (1969), Pospisil and Kasperek (1969), Burlet et al (1971), Parthasarathy and Govindarajan (1972), Hunter et al (1976), and Santhanam (1977), have shown that rotor yarn is weaker on average than ring yarn but, being more even, has better appearance and is relatively free of weak spots that may cause yarn breaks in later processes.

CHAPTER III

MATERIALS AND METHODS

3.1. Materials

The materials utilized in this study consisted of two long-staple cottons; Pima, (Gossypium barbadense L.), henceforth alluded to as (A), and a California variety, (Gossypium hirsutum L.) alluded to as (B), plus two short-staple G. hirsutum L. varieties, a West Texas fine (C), and a West Texas coarse (D). All of these cottons were sampled and tested for fiber properties at the sliver stage.

3.2. Preparation

Two samples of the long-staple cotton, weighing 110 lb each, were introduced into the Textile Research Center opening/cleaning/carding line, to produce card sliver. Because the waste expected to be removed in combing the short-staple cottons exceeds that of the long-staple types, 120 lb of C and D were fed to the opening hoppers. Total opening and carding waste as a percentage of the weight fed was measured as 6.7% and 9.5% for A and B, respectively, and 10.2% for C and D.

The card sliver of both long-staple and short-staple cottons was divided into two unequal parts, 45% and 55% of the card sliver weight, for carded and combed sliver, respectively.

For the coarse slivers, forty-five percent by weight of the card sliver was passed through two successive drawing processes by using the draw frame. The remaining fifty-five percent of the same card sliver was pre-drawn once, lap-formed, combed and drawn twice again before being rotor-spun.

The fine slivers all required an additional drawing for attenuation to 30 gr/yd. This introduced some short-term irregularity and raised sliver C.V. values (see Appendix). Moreover, Vaughn (1975) reported a yarn strength increase of two percent due to a third drawing. For these reasons, any comparisons of results between the two sliver weights are to be interpreted cautiously.

For setting counters to determine the length to be taken for different pre-spinning processes, the following equation was applied:

$$\frac{\text{weight of waste-free card sliver in grains}}{\text{sliver weight in grains/yard} \times \text{No. of ends}} = \frac{\text{counter setting}}{\text{in yards}}$$

3.2.1. Spinning

In the rotor spinning stage, sixteen cans were used, as follows:

1--Cans of 60-grains/yard sliver

a--four carded lots

b--four combed lots

2--Cans of 30-grains/yard sliver

a--four carded lots

b--four combed lots

The spinning process was carried out from the sixteen cans by using the rotor spinning machine BD 200-S to convert the slivers into yarns. Eight spinning positions were chosen, with the sliver samples arranged at random in front of each position.

3.2.2. Spinning Conditions

1--Rotor speed	was	46,400 r.p.m.
2--Opening roll speed	was	6,200 r.p.m.
3--Opening roll type	was	OK 40
4--Rotor diameter	was	54 mm
5--Navel type used	was:	

a--smooth for maximum strength at high twist

b--grooved for spinnability at low twist

The draft was calculated by applying the following equation:

$$\text{Draft} = \frac{\text{sliver weight (gr/yd)} \times \text{Yarn count (Ne)}}{8.33}$$

then adjusted if necessary after checking the yarn count of a 120-yd sample in the skein winder. On the basis of the adjusted draft, the exact value of yarn count was evaluated.

In general, twist (tpm) decreases with increasing tex count according to $t = k/\text{tex}^n$ where t is twist in turns/metre, k and n are constants. For present work, an exponent, n , of 0.60 was used.

High and low twists in turns/metre were calculated according to the two following equations, respectively, for

Ne 20, 30 and 45 (29.5, 19.7 and 13.1 tex, respectively):

High twist = $6700/\text{tex}^{0.6}$, i.e., 879, 1120 and 1429 tpm

Low twist = $4900/\text{tex}^{0.6}$, i.e., 643, 819 and 1045 tpm

Put another way, the simple twist multiplier, defined as turns/metre multiplied by $\sqrt{\text{tex}}$, was increased in proportion to $\text{tex}^{-0.1}$.

In addition, the spinning time and the number of yarn end-breaks at each spinning position were recorded.

3.2.3. Identification Code

Every cheese of yarn was identified by a six-digit code. Every one of the six digits identifies fiber, processing, sliver weight, yarn count, twist and replications, respectively.

The first digit of the identification code represents four levels of the cotton fibers.

1 = Pima

2 = California

3 = West Texas fine

4 = West Texas coarse

The second digit refers to processing: number 1 for the carded sliver, and number 2 for the combed sliver.

The sliver weight (60 or 30 grains/yard) was described by the number 1 or 2 in the third identified digit.

The fourth digit had the number 1, 2, or 3 according to the yarn count, 45s, 30s or 20s, respectively.

High and low twist were expressed by number 1 or 2 in

the fifth digit.

The last identification digit represents the first or second replication, according to the number (1 or 2).

Example:

identification code = 212111

2 = California cotton

1 = Carded sliver

2 = Fine sliver weight (30 gr/yd)

1 = Fine yarn count (45s)

1 = High twist

1 = First replication

The levels of each factor are summarized in Table 1.

TABLE 1
EXAMINED FACTORS AND THEIR LEVELS

Code	Factor	Levels	Remarks on Levels	
			Control	Experimental
F	Raw materials	4	West Texas coarse	Pima, California, West Texas fine
P	Processing	2	Carded only	Carded & combed
S	Sliver weight	2	60 gr/yd	30 gr/yd
C	Count	3	Ne 20	Ne 30, 45
T	Twist	2	High ("warp")	Low ("knit")
-	Replications	2	_____	_____

3.2.4. Fiber Tests

The cotton fibers were tested using the Motion Control High Volume Line (HVL), to measure:

1--Micronaire

2--Length

3--Uniformity ratio (UR)

4--Tenacity

3.2.5. Sliver Tests

The above-mentioned properties were investigated for cotton sliver, but a newly available Peyer instrument was used to measure length distribution. Both fiber length (2.5% span length in inches) and uniformity ratio were tested in accordance with corresponding ASTM standards. The Stelometer was used to re-examine fiber tenacity (g/tex).

In addition, fiber micronaire, hair weight (mtex) and maturity (%) data were measured by the Shirley/I.I.C. Fineness-Maturity Tester (FMT).

3.2.6. Yarn Tests

Yarn appearance was assessed according to ASTM D 2255-75, with each result based on the mean of three independent observers.

Each yarn evenness result is a single determination made on an Uster evenness tester at 100 m/min for 2.5 minutes, and thus represents 250 m of yarn.

Yarn strength was measured automatically in an Uster

Tensorapid instrument, with 25 breaks for each replicate. Thus, for instance, each of the four fibers was tested 1200 times; each sliver weight, 2400 times, making for a sensitive measure of factors affecting strength. Tenacity was calculated by dividing the mean strength by the nominal yarn count. Deviations between nominal and actual count were slight.

3.3. Design of the Experiment

A factorial design was used, primarily because of its capability of detecting both main effects and factor-interactions among studied factors.

Table 1 represents the factors and number of their levels; both control and experimental. With each combination repeated, there were 192 spinning experimental units, with corresponding tests of yarn properties.

Results of yarn end-breakage, evenness, and tenacity were logarithmically transformed for the following reasons:

1--to make the residual variance homogeneous

2--to avoid spurious interactions

The results of yarn appearance were not logarithmically transformed, however, because this property depends on eye response, which varies with the logarithm of the stimulus. This is confirmed by the fact that appearance results are already normally distributed. End-breakage rate/rotor hour (EDRH) was transformed into $\ln (1 + \text{EDRH})$.

CHAPTER IV

RESULTS

The present data illustrate the effect of five factors (raw material, preparation, sliver weight, yarn count and twist) on rotor-spun yarns of four different cottons (Pima, California, West Texas fine, and West Texas coarse).

The effect of combing on the fiber properties; mean length, coefficient of variation of length, the percent of long fibers >1.25", the short fibers <0.5", 50% and 2.5% span lengths, uniformity ratio, micronaire, maturity, hair weight, tenacity and the calculated number of fibers in the yarn cross-section, is shown in Table 2. These properties were measured on the sliver as spun, and their effects on spinning were assessed by four sets of measurements: appearance, end breakage rate, evenness and tenacity.

Table 2 represents the effect of carding (Q) and both carding and combing (R) on the properties of the cotton fibers. The percentage change due to combing (Z) is also illustrated. The AL-101 apparatus was used for all length measurements. The uniformity ratio (U.R.) of the sample was calculated according to the following equation:

$$\text{U.R.}(\%) = \frac{50\% \text{ span length}}{2.5\% \text{ span length}} \times 100$$

Micronaire, percent maturity and hair weight (mtex) were evaluated by using the Shirley/I.I.C. Fineness-Maturity

TABLE 2

EFFECT OF COMBING ON FIBER PROPERTIES
OF COTTON SLIVERS

		Pima	California	West Texas Fine	West Texas Coarse
Mean length (by number) (inch)	Q	0.9	0.87	0.63	0.75
	R	0.98	0.97	0.73	0.82
	Z	+ 9.0	+ 12.0	+ 16.0	+ 9.0
C.V. of length (% by number)	Q	39.9	35.9	44.7	35.4
	R	32.3	28.4	37.3	28.7
	Z	- 19.0	- 21.0	- 17.0	- 19.0
Long fiber > 1.25" (% by number)	Q	18.1	11.9	1.2	2.1
	R	21.0	16.6	2.5	2.8
	Z	+ 16.0	+ 40.0	+108.0	+ 33.0
Short fiber < 0.5" (% by weight)	Q	7.2	6.3	21.6	11.1
	R	3.2	1.5	12.2	5.0
	Z	- 56.0	- 76.0	- 44.0	- 55.0
50% span length (inch)	Q	0.46	0.45	0.33	0.38
	R	0.49	0.49	0.37	0.42
	Z	+ 7.0	+ 9.0	+ 12.0	+ 11.0
2.5% span length (inch)	Q	1.29	1.2	0.99	1.03
	R	1.31	1.24	1.04	1.05
	Z	+ 2.0	+ 3.0	+ 5.0	+ 2.0
Uniformity ratio (%)	Q	36.0	38.0	33.0	37.0
	R	37.0	40.0	36.0	40.0
	Z	+ 3.0	+ 5.0	+ 9.0	+ 8.0
Micronaire	Q	3.77	3.86	2.31	4.77
	R	3.93	4.07	2.53	4.82
	Z	+ 4.0	+ 5.0	+ 10.0	+ 1.0
Maturity (%)	Q	87.0	88.0	56.0	93.0
	R	90.0	85.0	64.0	97.0
	Z	+ 3.0	- 3.0	+ 14.0	+ 4.0
Hair weight (mtex)	Q	141.0	143.0	111.0	176.0
	R	143.0	159.0	113.0	175.0
	Z	+ 1.0	+ 11.0	+ 2.0	- 0.6
Tenacity (g/tex)	Q	33.4	25.5	20.7	24.1
	R	34.6	23.9	20.9	24.8
	Z	+ 4.0	- 6.0	+ 1.0	+ 3.0
No. of fibers in yarn cross-section when Ne = 45	Q	92.0	91.0	117.0	74.0
	R	91.0	82.0	115.0	74.0
	Z	- 1.0	- 10.0	- 2.0	0.0

Q carded

R carded and combed

Z percentage change due to combing

Tester (FMT). The Stelometer apparatus was utilized to measure the tenacity of the cotton fibers expressed as grams/tex at 1/8 -inch gauge length. The table also shows the calculated number of fibers in the yarn cross-section according to the following formula:

$$\text{No. of fibers} = \frac{\text{Tex of the yarn}}{\text{Tex of the fiber}}$$

In the fine yarn, only the fine West Texas cotton reached a standard of 100 fibers in the yarn cross section. The two West Texas cottons differed chiefly in micronaire value, about half of this difference being due to fineness, half to immaturity.

Table 3 illustrates the appearance of the cotton yarns. Measured letter grades were quantified according to the following table:

<u>Yarn Grade</u>	<u>Numerical Value</u>
A	130
AB	120
B	110
BC	100
C	90
CD	80
D	70

Intermediate grades were assigned numerical values between the above figures, e.g., B+ became 115, B- was 105.

Table 4 shows the effect of combing on the yarn end-

TABLE 3
COTTON YARN APPEARANCE

Sliver Weight	Count	Twist	Pima		California		W.T. Fine		W.T. Coarse	
			Carded	Combed	Carded	Combed	Carded	Combed	Carded	Combed
60 gr/yd	45s	HIGH	112	128	128	125	88	87	133	130
			125	117	122	127	107	85	122	132
		LOW	122	125	122	123	95	83	127	128
			112	125	130	125	83	83	121*	128
	30s	HIGH	123	127	123	130	110	100	130	132
			113	125	127	127	107	100	133	133
		LOW	125	118	117	122	107	110	130	135
			125	125	118	123	113	100	128	130
	20s	HIGH	130	130	133	127	97	123	132	133
			127	128	132	133	117	122	130	135
		LOW	132	130	127	130	117	117	132	128
			128	125	123	125	112	117	130	133
30 gr/yd	45s	HIGH	107	127	110	127	87	87	122	130
			110	118	113	128	83	98	132	133
		LOW	110	125	120	127	88	87	131*	133
			110	123	130	127	82	85	125*	133
	30s	HIGH	127	130	122	130	107	115	123	130
			115	132	125	130	102	133	123	110
		LOW	115	128	120	130	95	102	122	125
			117	127	115	122	107	103	127	132
	20s	HIGH	128	130	130	135	120	115	135	133
			128	133	130	130	115	113	128	135
		LOW	122	133	125	127	112	122	130	130
			128	125	133	132	112	112	123	127

* Substitutes for missing values

TABLE 4
YARN END-BREAKAGE RATE PER ROTOR HOUR

Sliver Weight	Count	Twist	Pima		California		W.T. Fine		W.T. Coarse	
			Carded	Combed	Carded	Combed	Carded	Combed	Carded	Combed
60 gr/yd	45s	HIGH	1.92	0.77	0.0	0.0	0.77	0.0	0.38	1.54
			1.92	0.38	0.0	0.0	1.15	0.0	1.92	0.77
		LOW	1.09	0.0	1.09	0.0	0.0	0.0	6.01	3.28
			0.55	0.0	1.09	0.0	4.37	0.55	7.00*	4.37
	30s	HIGH	0.50	0.0	0.0	0.0	0.0	0.0	0.0	0.0
			2.00	0.0	0.50	0.0	0.0	0.0	0.0	0.50
		LOW	0.0	0.0	2.67	0.0	0.67	0.0	0.67	0.67
			0.0	0.0	2.00	0.0	0.67	0.0	0.67	0.0
	20s	HIGH	0.0	0.0	0.0	0.0	2.53	0.0	1.27	0.0
			0.0	0.63	0.0	0.0	0.0	0.0	0.0	0.63
		LOW	4.27	0.0	0.0	0.0	0.85	0.0	1.71	0.0
			0.0	0.0	0.0	0.0	0.85	0.85	2.56	0.0
30 gr/yd	45s	HIGH	0.0	0.0	0.0	0.0	0.0	0.0	1.92	0.38
			0.0	0.0	0.0	0.0	0.0	0.0	3.08	0.38
		LOW	0.55	0.0	0.0	0.0	0.55	0.0	7.00*	3.83
			0.0	0.0	0.55	0.0	0.55	0.55	8.00*	2.19
	30s	HIGH	0.0	0.0	0.0	0.0	0.0	0.0	1.00	0.0
			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
		LOW	0.0	0.0	0.0	0.0	0.0	0.0	0.67	0.0
			0.0	0.0	0.67	0.0	0.0	0.0	2.67	1.33
	20s	HIGH	0.0	0.0	0.0	0.0	0.0	0.0	0.63	0.0
			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
		LOW	0.85	0.0	0.0	0.0	0.0	0.85	0.85	0.0
			0.0	0.0	0.85	0.0	0.0	0.0	1.71	0.0

* Substitutes for missing values

breakage rate per rotor hour under the previously mentioned conditions. The following equation was applied:

$$\text{End-breakage rate} = \frac{\text{No. of ends down}}{\text{No. of spinning hours} \times \text{No. of rotors}}$$

Tables 5 and 6 represent the yarn evenness and tenacity of the tested cottons expressed as C.V.% and g/tex by using the Uster evenness tester and Tensorapid, respectively. The effect of combing after carding on the fibers of different counts (45s, 30s, 20s) at the high and low twists was studied in both the coarse and fine slivers.

Table 7 summarizes the effect of tested factors on cotton yarn properties (appearance, end-breakage rate, evenness and tenacity). Analysis of variance was carried out using the TELEX 178 computer and applying the subprogram SPSS. The significance of main effects and all interactions was evaluated at three different levels.

Table 8 is a summary of the main factors (cotton fibers, preparation, sliver weight, count and twist) as measured by the properties (appearance, end-breakage, evenness and tenacity) of yarns produced from the four cotton types (Pima, California, West Texas fine, and West Texas coarse). Minimum significant difference between pairs of readings can be determined approximately from $\text{MSD} = t s \bar{x} \sqrt{\frac{2k}{N}} \approx s \bar{x} \sqrt{\frac{k}{24}}$ where s is the residual standard deviation of the logarithms

$\bar{x}$ is the mean reading in original units

k is the number of categories being compared

Pairs having any common superscript are not significantly

TABLE 5
YARN EVENNESS (C.V.%)

Sliver Weight	Count	Twist	Pima		California		W.T. Fine		W.T. Coarse	
			Carded	Combed	Carded	Combed	Carded	Combed	Carded	Combed
60 gr/yd	45s	HIGH	18.0	16.8	17.7	18.0	16.4	17.0	18.9	19.1
			16.6	17.2	18.1	17.7	17.1	16.7	19.4	19.3
		LOW	15.8	15.9	17.3	17.3	16.3	17.2	18.2	18.2
			16.2	16.0	17.3	17.5	17.6	17.5	19.2*	19.2
	30s	HIGH	15.2	15.5	15.6	15.7	16.0	15.3	16.8	17.6
			16.4	15.5	16.4	17.5	16.0	15.8	17.7	17.7
		LOW	14.1	14.5	15.9	15.3	15.0	15.4	16.1	16.5
			14.0	14.6	15.6	16.2	15.6	15.1	16.2	16.5
	20s	HIGH	14.3	13.4	14.8	14.3	16.4	14.6	17.0	15.2
			14.3	13.8	14.5	14.0	14.8	14.7	16.4	16.7
		LOW	14.1	13.9	15.3	14.6	16.4	15.4	15.7	15.4
			13.8	14.6	14.6	15.0	15.4	15.7	15.7	15.9
30 gr/yd	45s	HIGH	17.1	16.2	18.5	17.2	18.7	18.1	19.9	19.0
			17.0	16.6	18.6	17.6	18.2	17.2	20.5	20.1
		LOW	16.0	16.7	17.6	17.5	17.7	17.0	19.6*	19.2
			15.7	16.1	17.3	16.2	17.6	17.8	18.6*	17.6
	30s	HIGH	15.2	15.0	16.4	15.9	16.8	15.8	18.6	17.5
			15.5	14.6	16.5	15.8	17.4	16.4	18.4	16.7
		LOW	14.9	15.1	16.1	16.1	16.5	16.2	17.1	16.8
			15.1	14.5	15.5	15.4	16.8	15.9	17.7	16.0
	20s	HIGH	14.4	16.5	14.8	13.9	15.9	15.5	17.2	15.8
			14.8	14.0	15.2	15.0	16.3	15.7	19.3	15.8
		LOW	13.7	13.6	15.3	14.8	16.0	15.9	16.3	15.6
			14.4	13.8	14.9	14.8	16.6	16.2	16.8	17.1

* Estimated values

TABLE 6
YARN TENACITY (g/tex)

Sliver Weight	Count	Twist	Pima		California		W.T. Fine		W.T. Coarse	
			Carded	Combed	Carded	Combed	Carded	Combed	Carded	Combed
60 gr/yd	45s	HIGH	13.3	15.8	12.2	13.8	9.5	11.2	11.6	11.8
			14.2	15.2	11.1	13.7	10.5	12.4	10.9	13.2
		LOW	11.7	14.7	11.5	11.9	8.7	10.0	10.6	10.2
			11.9	14.8	10.7	11.6	9.2	11.8	8.0*	9.3
	30s	HIGH	15.7	16.1	13.1	14.6	11.2	13.6	11.9	13.4
			15.3	16.5	12.4	13.5	10.8	12.5	13.8	12.0
		LOW	13.4	15.5	12.4	12.7	9.8	13.3	8.6	10.9
			14.4	15.3	11.0	13.4	9.6	12.4	10.7	8.9
	20s	HIGH	14.8	17.6	13.3	14.8	11.8	13.3	12.3	13.1
			15.1	16.8	13.7	15.6	11.4	13.8	11.7	12.5
		LOW	14.3	17.1	11.7	13.8	10.9	10.8	9.7	11.6
			14.9	16.1	11.9	14.4	10.4	11.7	9.5	10.5
30 gr/yd	45s	HIGH	14.8	17.0	11.8	13.5	10.8	11.2	9.8	12.6
			14.9	15.3	12.9	14.7	11.9	13.3	12.3	13.0
		LOW	13.3	15.7	11.1	13.3	10.3	9.3	8.0*	9.6
			13.3	15.9	10.7	13.5	8.8	10.6	10.5*	10.2
	30s	HIGH	16.2	16.8	13.5	15.7	12.2	12.6	12.0	12.7
			15.6	17.0	12.6	13.9	11.0	12.6	11.3	13.6
		LOW	14.6	16.7	11.6	14.1	11.5	12.5	9.3	11.3
			15.1	16.5	11.2	13.0	10.6	12.4	10.2	11.5
	20s	HIGH	17.5	18.1	13.8	16.6	12.3	13.6	13.6	15.0
			16.8	18.7	13.7	15.4	12.4	12.1	11.9	14.1
		LOW	15.7	16.5	11.8	13.8	10.1	12.1	10.6	11.7
			15.3	17.1	12.2	14.9	10.9	11.3	9.5	9.8

* Substitutes for missing values
Estimated values

TABLE 7
SUMMARY OF ANALYSES OF VARIANCE

Effect	d.f.	Appearance		Breakage Rate		Evenness		Tenacity	
		F ratio	Sig.	F ratio	Sig.	F ratio	Sig.	F ratio	Sig.
Main effects									
F	3	280.00	.000	32.70	.000	158.00	.000	271.00	.000
P	1	23.90	.000	50.60	.000	19.50	.000	159.00	.000
S	1	1.48	.222	16.10	.000	22.40	.000	16.10	.000
C	2	87.30	.000	22.60	.000	346.00	.000	48.70	.000
T	1	5.86	.016	29.30	.000	28.70	.000	183.00	.000
Two-factor interactions									
FP	3	1.92	.124	1.90	.327	1.45	.226	1.41	.236
FS	3	0.61	.604	2.08	.071	4.94	.003	0.96	.406
FC	6	24.70	.000	11.50	.000	4.68	.000	1.07	.375
FT	3	0.68	.557	10.10	.000	5.49	.001	12.20	.000
PS	1	12.10	.001	4.22	.000	8.68	.004	0.19	.664
PC	2	0.75	.467	1.25	.545	1.08	.337	0.19	.825
PT	1	0.95	.326	7.05	.008	5.81	.017	0.91	.338
SC	2	0.39	.671	0.85	.535	1.06	.341	0.10	.889
ST	1	0.05	.820	0.30	.723	0.24	.621	0.01	.909
CT	2	0.91	.398	2.06	.214	5.85	.004	1.13	.321
Three-factor interactions									
FPS	3	1.47	.219	5.05	.000	1.83	.140	3.30	.022
FPC	6	2.12	.053	1.19	.296	0.47	.822	0.88	.502
FPT	3	0.43	.722	1.32	.282	0.12	.949	0.49	.686
FSC	6	2.23	.043	1.38	.194	0.40	.874	0.36	.895
FST	3	2.31	.076	1.25	.297	0.52	.659	0.07	.973
FCT	6	1.83	.094	3.97	.001	0.86	.514	0.64	.688
PSC	2	3.38	.036	0.08	.997	2.06	.127	0.33	.716
PST	1	0.08	.774	1.70	.190	0.10	.753	0.01	.909
PCT	2	0.02	.982	0.44	.638	0.41	.662	0.68	.501
SCT	2	2.31	.100	0.31	.875	3.27	.040	1.54	.212
Higher-order interactions									
	28	1.45	.110	1.40	.170	1.03	.400	0.69	.860

F Fiber
 P Preparation
 S Sliver weight
 C Count
 T Twist
 d.f. Degrees of freedom
 Sig. Probability of F-ratio being exceeded by chance; significance level

TABLE 8
SUMMARY OF MAIN EFFECTS

		APPEARANCE	BREAK RATE (per rotor hour)	EVENNESS (%)	TENACITY (g/tex)
Fiber Effects					
Pima		123 ^c	.20 ^a	15.18 ^a	15.45 ^a
California		126 ^b	.13 ^a	16.06 ^b	13.01 ^b
W.T. fine		103 ^d	.21 ^a	16.33 ^c	11.32 ^c
W.T. coarse		129 ^a	.90 ^b	17.51 ^d	11.16 ^c
Preparation Effects					
Carded		119 ^b	.54 ^b	16.42 ^b	11.91 ^b
Combed		121 ^a	.16 ^a	16.08 ^a	13.37 ^a
Sliver-weight Effects					
60 gr/yd		120 ^a	.44 ^b	16.07 ^a	12.39 ^b
30 gr/yd		120 ^a	.23 ^a	16.43 ^b	12.86 ^a
Count Effects					
Ne 45		115 ^c	.62 ^b	17.64 ^c	11.87 ^c
Ne 30		120 ^b	.19 ^a	15.99 ^b	12.79 ^b
Ne 20		126 ^a	.22 ^a	15.22 ^a	13.24 ^a
Twist Effects					
High		121 ^a	.19 ^a	16.45 ^b	13.43 ^a
Low		119 ^b	.49 ^b	16.05 ^a	11.86 ^b
Residual Standard Deviation	in logarithms	————	.288	.032	.064
	in original units	4.88 ±one-quarter grade	±0.38 EDRH	0.53 percen- tage	0.81 g/tex

Means having any common superscript are not significantly different at the 5% level.

different at the 5% level.

Three yarns could not be spun to a count of Ne 45 with low twist from carded material of Lot D, the coarse West Texas cotton, both replicates from the fine sliver and one from the coarse sliver. Such yarns as were made from these broke repeatedly in spinning and contained so much seed yarn that any tests on them would have been invalid.

To complete the analysis of variance, these missing values were calculated in the usual manner except that the result in the same cell was assigned high and low values to give two replicates having the same variance as the average residual variance. These missing values caused the number of laboratory measurements to be reduced from 192 to 189, the residual degrees of freedom from 96 to 94, and the degrees of freedom in the highest-order interaction from 6 to 5. This procedure always causes the analysis to err on the conservative side, possibly overlooking some effects but avoiding the risk of detecting false effects.

CHAPTER V

DISCUSSION

This chapter describes all significant interactions including any corresponding lower-order interactions and main effects, which are not discussed further, except descriptively in Table 8. M.S.D. is the minimum significant difference based on the logarithms used in the analysis. This is the most exact criterion.

5.1. Yarn Appearance

Because the test uses different photographic standards for the three counts, any differences between counts are to be interpreted cautiously.

5.1.1. Preparation X Sliver Weight X Count Interaction

Combing significantly improves yarn appearance, but only at fine and medium counts (45s and 30s) with fine sliver. This improvement of yarn appearance by combing is in accordance with Srinathan et al (1976), as shown from Table 9.

TABLE 9

YARN APPEARANCE: PREPARATION X SLIVER
WEIGHT X COUNT INTERACTION

Sliver Weight	Count (Ne)	Preparation	
		Carded	Combed
Coarse	45	116	116
	30	121	121
	20	125	127
Fine	45	110	118
	30	116	124
	20	125	127

M.S.D. = 3.4

5.1.2. Fiber X Sliver Weight X Count Interaction

In general, the best yarn appearance was observed in W.T. Coarse cotton at all yarn counts, but especially with coarse sliver (60 gr/yd). Improving yarn appearance by using W.T. coarse cotton may be attributed to the coarseness and maturity of the fiber, which tends to decrease the number of neps in the yarn. This cotton gave better appearance than any other with 45s yarn and fine sliver, as shown from Table 10.

TABLE 10

YARN APPEARANCE: FIBER X SLIVER
X COUNT INTERACTION

Sliver Weight	Count (Ne)	Cotton Fibers			
		Pima	California	W.T. Fine	W.T. Coarse
Coarse	45	121	125	89	128
	30	123	125	106	131
	20	129	129	115	132
Fine	45	116	123	87	130
	30	124	124	108	124
	20	128	117	115	130

M.S.D. = 4.8

5.1.3. Effect of Twist on Yarn Appearance

As shown from Table 8, high twist with a smooth navel gave significantly better yarn appearance than low twist with a grooved navel. There were no significant interactions involving twist, one of only two instances in the experiment in which an unqualified main effect was identified. The main effect (Table 8) indicated a quite general improvement in appearance at the higher twist. This consistency confirms that the two twists selected for each of the three quite different counts were appropriate.

5.2. End-Breakage Rate

The results were not normally distributed, because of the number of trials in which no breaks occurred. Therefore, only effects showing a significance level below 3% are discussed.

5.2.1. Fiber X Count X Twist Interaction

Apart from the extraordinarily high rate for the coarse W.T. cotton at low twist, all counts show similar rates of end break, with the lower twist consistently causing more breaks, especially in the coarse W.T. cotton. The findings indicate that high twist improved yarn end-breakage rate. This confirms the results of Coll-Tortosa and Phoa (1976), who reported that higher twist values are one answer to the problems of increasing end-breakage rate, but this is not true of the long Pima cotton, as shown from Table 11.

5.2.2. Fiber X Preparation X Sliver Weight Interaction

Table 12 shows that reducing the sliver weight greatly reduces the rate of end breaks, although with combed W.T. fine and California cottons, the rate is already so low that the effect is negligible. Combing is likewise beneficial, though the effect is not significant in fine W.T. cotton from fine sliver. On average, combing reduced the end-break rate by a factor of 3.5, and halving the sliver weight halved the rate of end breaks. Work loads in rotor spinning can therefore be increased if the sliver is attenuated and the fiber is combed.

TABLE 11

END-BREAKAGE RATE: FIBER X COUNT X
TWIST INTERACTION

Twist	Fiber	Count (Ne)		
		45	30	20
High	Pima	0.47	0.21	0.07
	California	0.0	0.05	0.0
	W.T. Fine	0.18	0.0	0.18
	W.T. Coarse	0.96	0.15	0.25
Low	Pima	0.21	0.0	0.33
	California	0.25	0.44	0.08
	W.T. Fine	0.51	0.13	0.35
	W.T. Coarse	4.97	0.67	0.63

M.S.D. $\approx$ 0.38 EDRH

TABLE 12

END-BREAKAGE RATE: FIBER X PREPARATION
X SLIVER INTERACTION

Sliver Weight	Fiber	Preparation	
		Carded	Combed
Coarse	Pima	0.72	0.12
	California	0.42	0.0
	W.T. Fine	0.72	0.09
	W.T. Coarse	1.20	0.66
Fine	Pima	0.09	0.0
	California	0.13	0.0
	W.T. Fine	0.07	0.09
	W.T. Coarse	1.59	0.44

M.S.D. $\approx$ 0.31 EDRH

5.3. Yarn Evenness

In general, yarn evenness results were poor, near the Uster provisional 75% level (Zellweger Uster, 1982, p. 34). This is, however, typical of tests in which the wrapper fibers are redistributed in the hairiness measurement which comes before the evenness test.

5.3.1. Sliver X Count X Twist Interaction

Table 13 shows that higher twist impairs evenness, but in conventional rotor spinning, where a heavy sliver is used to make a coarse yarn, this effect is not significant. Consequently, the advent of fine-yarn spinning, and the use of finer sliver to reduce draft, may cause more irregularity than is at present apparent to manufacturers, especially when high twist is applied in an effort to maximize yarn strength in fine yarns. Barella et al (1983), testing Ne 12 and 16 yarn, reported that twist has no influence on yarn irregularity (two machines were used in their study, Süssen and SKF). This result confirms our finding at Ne 20.

5.3.2. Preparation X Twist Interaction

Table 14 shows that the tendency for evenness to improve at low twist is more pronounced in carded than in combed fiber. Combing has a better effect on yarn evenness at high twist. Thus, in general, lower twist gives better yarn C.V.

TABLE 13

EVENNESS: SLIVER X COUNT X
TWIST INTERACTION

Count (Ne)	High Twist		Low Twist	
	Sliver Weight (gr/yd)			
	60	30	60	30
45	17.74	18.12	17.29	17.42
30	16.25	16.36	15.40	15.95
20	14.90	15.58	15.07	15.32

M.S.D. = 0.37%

TABLE 14

EVENNESS: PREPARATION X
TWIST INTERACTION

Twist	Preparation	
	Carded	Combed
High	16.78	16.19
Low	16.12	15.96

M.S.D. = 0.21%

5.3.3. Preparation X Sliver Weight Interaction

Table 15 shows that coarse sliver gave better evenness, but only in carded yarn. This implies that spinners could achieve better yarn evenness by choosing coarse slivers to be spun on rotor machines. Attenuating the sliver, despite a substantial reduction in end breakage, did increase yarn irregularity, especially in carded sliver. Because drawing was done without autoleveling, there is potential for greatly improving the evenness values quoted in the appendix, hence the yarn evenness, especially from fine sliver.

TABLE 15

EVENNESS: PREPARATION X SLIVER
INTERACTION

Preparation	Sliver Weight	
	60 gr/yd	30 gr/yd
Carded	16.12	16.78
Combed	15.96	16.12

M.S.D. = 0.21%

5.3.4. Fiber X Twist Interaction

Low twist improved yarn evenness only in Pima and West Texas coarse cottons. Evenness of yarns from the ordinary rotor-type cottons could not be improved much by reducing twist. But, in general the long-staple cottons (Pima and

California) gave better yarn evenness than the short-staple cottons (W.T. fine and W.T. coarse) especially at low twist, as shown from Table 16.

TABLE 16
EVENNESS: FIBER X TWIST INTERACTION

Fiber	Twist	
	High	Low
Pima	15.49	14.88
California	16.12	15.96
W.T. Fine	16.28	16.28
W.T. Coarse	17.81	17.12

M.S.D. = 0.30%

5.3.5. Fiber X Count Interaction

Table 17 shows that coarse count (20s) gave the best yarn evenness with Pima, California, and coarse W.T. cottons, but less so in fine W.T. cotton. In general, the best result was obtained at 20s with Pima Cotton; even at 30s and 45s Pima is still superior in yarn evenness when compared with the other three cottons. This result confirms that of Stalder (1979), who stated that the unevenness of rotor-spun yarns reaches a minimum with fiber lengths of approximately 40 mm. On the other hand, the present results contradict that of Lünenschloss and Hummel (1968), who reported that

short-staple cottons give better yarn evenness. The effect of increasing yarn fineness is to raise the C.V., less so in the W.T. fine fiber.

TABLE 17
EVENNESS: FIBER X COUNT INTERACTION

Fiber	Count (Ne)		
	45	30	20
Pima	16.50	14.95	14.19
California	17.58	15.98	14.74
W.T. Fine	17.37	15.98	15.68
W.T. Coarse	19.20	17.11	16.34

M.S.D. = 0.37%

5.3.6. Fiber X Sliver Weight Interaction

Coarse sliver gave better yarn evenness with fine W.T. and coarse W.T. cottons. For the longer cottons, evenness was independent of sliver weight, as shown from Table 18.

5.4. Yarn Tenacity

Results were generally good, near the Uster provisional 25% level (Zellweger Uster, 1982, p. 37).

5.4.1. Fiber X Preparation X Sliver Interaction

Table 19 shows that the effect of combing is greater for fine W.T. cotton in coarse sliver, least for W.T. fine in

TABLE 18
EVENNESS: FIBER X SLIVER
INTERACTION

Fiber	Sliver Weight	
	60 gr/yd	30 gr/yd
Pima	15.13	15.24
California	16.03	16.09
W.T. Fine	15.95	16.72
W.T. Coarse	17.24	17.78

M.S.D. = 0.30%

TABLE 19

TENACITY: FIBER X PREPARATION X
SLIVER INTERACTION

Preparation	Fiber	Sliver Weight	
		Coarse	Fine
Carded	Pima	14.06	15.21
	California	12.05	12.20
	W.T. Fine	10.27	11.01
	W.T. Coarse	10.66	10.69
Combed	Pima	15.93	16.72
	California	13.59	14.32
	W.T. Fine	12.18	11.91
	W.T. Coarse	11.36	11.98

M.S.D. = 0.57 g/tex

fine sliver. In general, the best yarn tenacity was obtained from fine combed sliver of Pima cotton. The improved yarn tenacity in long-staple Pima cotton is in agreement with Chukaev and Manakova (1972), and researchers at Texas Tech University (1980). Reducing the sliver weight, hence the draft in the opening roll, makes a substantial improvement to yarn strength, but the effect is slight in the shorter cottons. The longer cottons respond better to the lower sliver weight, but the beneficial effect of combing is apparent even in the short-staple fiber.

5.4.2. Fiber X Twist Interaction

Table 20 shows that high twist gave high yarn tenacity in all the four cottons used in the study. The W.T. coarse cotton was the most sensitive to twist.

Morikawa and Hariwuchi (1968) stated that yarn produced from the BD 200 rotor spinning machine showed greatest strength at a twist about 15% above the "high" level of the trials reported here. As expected, increasing the twist improves tenacity of the short coarse cottons the most.

5.4.3. Effect of Count on Yarn Tenacity

As shown from Table 8, the yarn has a higher tenacity at coarse count (20s), and as the yarn gets finer the tenacity significantly decreases. This explains the higher breakage rate for the yarn at very fine count (45s).

TABLE 20
TENACITY: FIBER X TWIST INTERACTION

Twist	Fiber			
	Pima	California	W.T. Fine	W.T. Coarse
High	16.00	13.68	11.95	12.44
Low	14.92	12.37	10.72	10.01
Percentage Increase	7.2	10.6	11.5	24.3

M.S.D. = 0.43 g/tex

When compared with Uster Tenacity Standards, our tenacity results in Table 8 appeared better in yarn tenacity as follows:

Count (Ne)	Measured Tenacity (g/tex)	Uster Median Standard (g/tex)
45	11.87	—
30	12.79	11.40
20	13.24	11.00

Whereas the same materials and processing were used in the present research, the Uster provisional experience values are based on industrial practice, varying from mill to mill. Plants spinning fine counts can generally be expected to have more modern machinery, higher quality standards and better raw materials than conventional coarse-yarn

rotor-spinning mills. Thus, the strength improvement in fine counts shown in the Uster values does not necessarily imply that a given spinner will find higher tenacity when it makes fine yarns. In the present study, with the above factors held constant, a steady decrease in tenacity was observed as count became finer.

CHAPTER VI

CONCLUSIONS

The results of this study indicate a number of significant two- and three-factor interactions in all four yarn properties.

The results can be summarized as follows:

1. Lowering the twist improved yarn evenness especially in the finer counts, but impaired yarn appearance generally. The end-breakage rate of the coarse short cotton at the finest count was especially sensitive to twist. The higher twist greatly increased the strength of yarns from the two short cottons, but the response to twist in the long-staple types was slight because of their lower twist requirements.
2. Reducing the sliver weight had no effect on the end-break rate of W.T. coarse cotton, but the average effect on the other three fibers was a reduction of 60%. Yarn appearance was improved by using a fine sliver, but only if the sliver had been combed. For carded sliver, coarse sliver gave better yarn appearance. Yarn evenness was generally worse especially in the coarse yarn. Tenacity was little affected, though the Pima cotton gave stronger yarn

when spun from fine sliver. `

3. Combing is beneficial in improving yarn appearance, especially at fine and medium counts (45s and 30s). Generally, combing reduced the end-breakage rate by a factor of 3.5, and can be expected to improve the spinnability of fine rotor yarns. Combing exerted a positive effect on yarn evenness at high twist, and improved yarn tenacity of long-staple Pima cotton. Even the shorter cottons were improved in all respects by combing, because of the removal of short fibers.
4. The finest count showed a high end-breakage rate. Yarn evenness deteriorated steadily as the yarn became finer.
5. Yarn tenacity decreased as the yarn count became finer; this was a main effect that was independent of the other four factors.
6. Using a low-micronaire cotton impaired yarn appearance, but improved yarn end-breakage rate, especially at high twist. It also improved yarn evenness relative to W.T. coarse cotton. Yarn tenacity was improved at low twist in W.T. fine cotton compared with W.T. coarse cotton. However, neps from low-micronaire cotton were so abundant and thick that they could not be concealed in the fine count, which had unsatisfactory appearance.

7. Using long-staple cottons (Pima and California) reduced end-breakage rate, especially in California cotton, at high twist and at all three counts. Long-staple cottons improved yarn evenness, particularly at low twist and coarse count. The yarn tenacity was higher in Pima and California cottons compared with W.T. short-staple cottons, especially at high twist.

REFERENCES

- American Society for Testing and Materials, 1978. Annual Book of ASTM Standards, Part 32, pp. 412-417, Philadelphia, ASTM.
- Artzt, P. and Schenek, A., 1977. Minimum twist factor as a reference value for spinning stability during rotor spinning. *Textil Praxis International*, 32, (8):910-911 & VII-VIII.
- _____, and Hehl, R., 1978. Effects on material and spinning technology when producing tricot yarns by the OE rotor spinning process. *International Textile Bulletin, Spinning* (3):297-314.
- Audivert, R., 1980. Effect of the twist and the percentage extension on the elastic properties of open-end-spun yarns. *Investigacion e Informacio Textil de Tensioactivos*, 23, (1/2):10-13.
- _____, 1981. Technical note on the twist/strength curve of open-end-spun cotton yarns. *Investigacion e Informacion Textil de Tensioactivos*, 24, (3):225-226.
- _____, and Castellar, M. D. De, 1981. Effect of card sliver orientation and compactness on the mechanical properties of rotor-spun cotton yarns. *Investigacion e Informacion Textil de Tensioactivos*, 24, (4):299-304.
- Avrorov, V. A., and Privalov, I. S., 1983. Use of automatic manipulators for eliminating yarn breakage on rotor open-end spinning machines. *Tekhnologiya Tekstilnoi Promyshlennosti*, 4, (154):9-12.
- Barella, A., and Manich, A. M., 1981. Relation between the twist and resistance to repeated extensions of cotton rotor-spun yarns. *Journal of the Textile Institute*, 72, (4):186-187.
- _____, Castro, L., and Hunter, L., 1984. Diameter of ring-spun and rotor-spun cotton yarns: relation between the diameter and the properties of the fiber and of the yarn. *Revista de la Industria Textil*, (214):37-56.

- _____, Marino, P. N., and Garofalo, J., 1982. Investigations regarding yarn diameter and hairiness of cotton open-end rotor yarns. *Melliand Textilberichte*, 63, (11):749-753.
- _____, 1983. Factorial studies in rotor-spinning. I. Cotton yarns. *Journal of the Textile Institute*, 74, (6): 329-339.
- _____, and Torn, J., 1969. A contribution to the comparative study of the properties of open-end and conventional yarns. *Investigacion e Informacion Textil*, 12, (1): 21-33.
- _____, and Vigo, J. P., 1970. Critical twist values in break-spun yarns. I. Twist/breaking strength curve. *Investigacion e Informacion Textil*, 13, (4):483-499.
- Borzunov, I. G., and Puzanova, N. V., 1978. Research on the process of feed sliver preparation for rotor spinning by reducing the number of drawframe passages. *Sbomik Vedeckych Praci VSST 8 Liberci*, (11):335-342.
- Bruggeman, J. P., 1979. Study of some African cottons in classical and open-end spinning. *Industrie Textile*, (1086):127-133.
- Brunk, N., 1982. Rotor open-end-spun yarns from the fine fibers--production and end-uses. *Textiltechnik*, 32, (2):93-96.
- Bruno, G. P., 1980. Are there any fundamental reasons for not introducing combing into a system of rotor spinning? *Industria Cotoniera*, 33, (3):191-197.
- Burlet, J. E., Deronne, P., and Lava, G., 1971. Break-spinning on the Czech BD 200. II. Industrial trials on the BD 200 spinning machine. *Bulletin de l'Institut Textile de France*, 25, March/April:173-187.
- Catling, H., 1983. A history of spinning and weaving. *Textiles*, 12, (1):20-28.
- Chemie, J., and Kowalski, J., 1983. Processing of R3 cotton on rotor open-end spinning machines. *Przeglad Wlokienniczy*, 37, (7,8,9):298-299.
- Chukaev, Yu., and Manakova, A. P., 1972. Length of cotton fibers for yarns obtained by pneumomechanical spinning. *Tekstil'naya Promyshlennost'*, 32, (9):36-37.

- Cizek, L., 1968. Experience gained in open-end spinning operation. *Kovoexport*, 14, (11):7-9.
- Coll-Tortosa, L., and Phoa, T. T., 1976. Origin and effect of false twist in rotor spinning machines. 'Textos de la Jornada de Informacion sobre Hilatura open-end' (AITA):43-57.
- Czaplicki, Z., 1973. Effect of the secondary wall of cotton fibre on the number of faults in a web and on the irregularity of yarn spun with the ring and open-end systems. *Przeglad Wlokienniczy*, 27, (4):178-183.
- Delerm, J. C., 1976. Quality and adaptability in a rotor spinning department. *Textil Praxis International*, 31, (5):490-491.
- Douglas, K., 1972. Yarn quality--OE vs Ring. *Textile Industries*, 136, (11):55-59.
- El-Messiry, M. A., 1977. Open-end spinning and labour requirements. *Magyar Textiltechnika*, (1):4-8.
- Feigenberg, A. L., Toroptsev, V. A., and Khudyakova, N. A., 1970. Improving the quality and reducing the breakage frequency of yarn on BD-200 machines. *Tekstil'naya Promyshlennost'*, 30, (8):41-43.
- Frey, M., 1974. Selected aspects of open-end spinning. *Textil Praxis International*, 29, (2):160-167.
- Gupte, A. A., Jayram, V. S., And Vinzanekar, S. G., 1981. Combing results of Indian cottons. *Indian Textile Journal*, 91, (7):117-122.
- Herold, H., 1976. Rational production and use of rotor-spun yarns. *Textil Praxis International*, 31, (9):963-964, 969-970 & V-VII.
- Hom, M., 1974. Reducing the amount of twist in yarns spun on BD open-end machines. *Textiltechnik*, 24, (7):406-408.
- Hunter, L., Aldrich, D. V. , and Andrews, G., 1976. Comparison of open-end and ring spinning. I. The physical properties of 25-tex yarns spun from different cottons grown in Southern Africa. South Africa Wool and Textile Research Institute of the CSIR, 18 pages, S.A.W.T.R.I. Publication No. 328.
- Jain, P. S., and Marwaha, G. L., 1975. Open-end spinning-- Does it satisfy the Indian techno-economic requirement? *Journal of the Textile Association*, 36, (4):163-170.

- Kasperek, J. V., 1968. Uniformity and strength of yarn produced by spindleless spinning. *Tekh. Tekstil. Prom.*, 1, (62):16-20.
- _____, 1968. Evenness of break-spun yarn. *Textile Manufacturer*, 94, December:484-488.
- Kluka, A., and Wojciechowski, M., 1973. Effect of feed sliver preparation on the proper running of the spinning process on an open-end spinning machine. *Technik Wlokieniczny*, 22 (2):45-50.
- Kochetkova, T. S., and Kovacheva, M. V., 1976. Changes in the properties of cotton fibers during open-end spinning. *Tekstil'naya Promyshlennost*, 36, (5):32-33.
- Konishi, T., 1976. Textiles in Japan--with particular reference to OE spinning. *Textile Month*, September: 40-41, 69.
- Krause, H. W., and Soliman, H. A., 1970. Open-end spinning. Fiber preparation by roller drafting. *Melliand Textilberichte International*, 51, (9):998-1000.
- _____, 1971. Unevenness adjustment by fiber deposition in the open-end turbine. *Textil-Industrie*, 73, (4):216-219.
- Landwehrkamp, H., 1979. Influence exerted by the preparatory operations and the sliver weight on the production of fine rotor-spun yarns. *Melliand Textilberichte*, 60, (11):912-916.
- Lennox-Kerr, P., 1974. OE--The reality is that it could spin about 30% of world yarn needs. *Textile Manufacturer*, 101, (17):19-21.
- _____, 1979. Rotor-spun count range growing, now includes a fine Ne 54.00. *Textile World*, 129, (8):52.
- Locher, H., and Kasperek, J., 1967. An Uster analysis of open-end spun yarn from Czechoslovakia. *Industrie Text.*, (959):501-505.
- _____, 1967. An Uster analysis of the Czechoslovakian open-end yarn. *Melliand Textilberichte*, 48, (8):869-873.
- Lord, P. R., 1971. The structure of open-end-spun yarn. *Textile Research Journal*, 41, (9):778-784.
- _____, 1974. Yarn evenness in open-end spinning. *Textile Research Journal*, 44, (7):512-515.

- Louis, G. L., 1978. Grading open-end spun cotton yarns. America's Textiles: Reporter/Bulletin Edition, AT 7, (4):88-91.
- Lünenschloss, J., Coll-Tortosa, L., and Phoa, T. T., 1975. Influence of the fiber length and the fiber length distribution on the properties of open-end rotor-spun yarns from cotton. II and III. Textil Praxis International, 30, (3):280-282, 399-402.
- Lünenschloss, J., and Hummel, E., 1968. Comparative studies on open-end and ring-spun yarns. Textil-Praxis, 23, (9):591-597.
- Lünenschloss, J., and Kampen, W., 1976. Influence of the number and formation of wrapped fibers on the properties of rotor-spun yarns. Textil Praxis International, 31, (11):1274, 1279-1280; (12):1394-1396.
- Manich, A. M., and Barella, A., 1984. Apparent loss of yarn twist in rotor spinning. Melliand Textilberichte, 65, (5):301-304.
- Mitova, B., 1981. Study on the effect of twist on the abrasion resistance of yarns produced by rotor open-end spinning. Textilna Promishlennost, 30, (7):297-300.
- Morikawa, T. and Hariwuchi, T., 1968. On the quality of BD yarn, and its end-uses, mass-produced by Japanese made 'BD-200'. Journal of the Textile Machinery Society of Japan, 21, (11):721-728.
- Nikolic, M., 1980. Comparison of conventional and open-end spinning. Tekstil, 29, (4):239-245.
- Parthasarathy, M. S., and Govindarojan, S., 1972. Studies on open-end spinning. Proceedings. Thirteenth Technological Conference, 1:91-100.
- Pillay, K. P. R., 1975. Use of open-end spinning for short staple cottons. Textile Research Journal, 45, (6):493-499.
- Polyakova, D. A., 1980. Selecting the setting parameters for a rotor open-end spinning machine. Tekstil'naya Promyshlennosti', 40, (10):27-28.

- Pospisil, F., 1976. BD 200 RC rotor spinning machine. Investa, 7, (6):2-6.
- Pospisil, Z., and Kasperek, J. V., 1969. Properties, processing and application of break-spun yarns. Textile Weekly, 69, (1):472-477, 513.
- Pützscher, F., 1976. Large-scale production on BD 200 rotor open-end spinning machines in the cotton industry of East Germany. Melliand Textilberichte International, 57, (3):177-181.
- Rohlena, V., 1974. Open-end spinning: Main factors affecting yarn and fabric production and their economy. Seventh Shirley International Seminar, Shirley Institute, 14 pages.
- _____, 1977. Progress in rotor spinning. Investa, 8, (3):2-5.
- S.A.C.M., 1967. Break spinning machine from France. Text. Rec., 85, December:51-52.
- Santhanam, K., 1977. Properties of yarns spun on open-end spinning frame and conventional ring frame--a comparative study. Man-made Textiles in India, 20, (5):31-39.
- Seshan, K. N., Pillay, K. P. R., Ratnam, T. V., and Govindarajan, S., 1979. 'Cotton in a Competitive World', The Textile Institute, Manchester, p. 202.
- Shcherbakova, N. A., Vozzhanikova, Z. I., and Vladyzhenskaya, A. A., 1983. Mill trials on PR-150-1 [rotor open-end spinning] machines. Tekstil'naya Promyshlennost', 43, (9):34-35.
- Shimizu, E., Inoue, T., Ido, H., and Noguchi, H., 1968. The special features of the yarn produced by the rotor spinning method. Journal of the Textile Machinery Society of Japan, 21, (11):729-735.
- Simpson, J., 1978. Don't throw away one-third of your cards. Textile World, August:37-38.
- Srinathan, B., Ramanathan, S., Sundaram, V., and Parthasarathy, M.S., 1976. Effect of combing on spinning performance of quality cottons. Indian Textile Journal, 86, (8):87-92.

- Stalder, H., 1972. Will rotor-spinning supplement or replace the conventional process? Papers of the 57th Annual Conference of the Textile Institute:157-174.
- _____, 1979. Spinning fine yarn counts on OE rotor machines. International Textile Bulletin--Spinning, 2:155-173.
- Starodubov, A. A., 1981. Study of yarn formation during mass piecing-up on BD 200 M-69 machines and the most important quality criteria of the piecings. Tekhnologiya Tekstil'noi Promyshlennosti, 4, (142):30-33.
- Sultan, M. A., and El-Hawary, I. A., 1974. A comparison of the properties of open-end-spun and ring-spun yarns produced from two Egyptian cottons. Journal of the Textile Institute, 65, (4):194-199.
- Texas Tech University, 1978. Open-end spinning. Textile Topics, (4):2 pages.
- _____, 1978a. Effects of drawing on O-E single yarn strength. Textile Topics, 6, (8):6 pages.
- _____, 1978b. [Open-end spinning tests on cotton]. Textile Topics, 6, (5): 14 pages.
- _____, 1980. Spinning limit test on Elitex BD 200 S. Textile Topics, 8, (11):3 pages.
- _____, 1980. High strength cotton for open-end spinning. Textile Topics, 8, (9):3 pages.
- _____, 1981. Open-end spinning research. Textile Topics, 9, (11), (12), (1), (2):2 pages, 5 pages, 5 pages & 5 pages.
- _____, 1984a. Open-end spinning research. Influence of rotor groove dimensions. Textile Topics, 12, (10): 4 pages.
- _____, 1984b. Fiber tenacity/yarn strength relationship. Textile Topics, 12, (9):2 pages.
- Tiranov, V., Trueitsev, N. N., and Fransen, T., 1977. Comparative analysis of deformation characteristics of ring and open-end yarn. Annales Scientifiques Textiles Belges, 25, (2):178-184.

- Towery, J. D., 1976. OE spinning--fiber effects. Textile Industries, 140, April:66, 68-69.
- _____, 1976. Knitting yarns from open-end spinning. Annales Scientifiques Textiles Belges, 24, (2):185-201.
- Tyukov, B. A., Sharychenkov, A. A., Ivanov, G. M., and Yakupov, R. Sh., 1981. New model rotor open-end spinning machine. Tekstil'naya Promyshlennost', 41, (8): 33-34.
- Vaughn, E. A., 1975. The effects of cotton fiber properties on the quality of open-end yarns. Proceedings of Technical Seminar on Open End Spinning and Its Implications for Cotton, Lubbock, September:22-23.
- _____, and Rhodes, J. A., 1977. Right process, fiber length improve OE. Textile World, 127, March:75-77.
- Vila, F., Pey, A., and Barella, A., 1982. Influence of the preparation in open-end spinning of cotton. Comparative study of four processes. I. Bulletin Scientifique de l'Institut Textile de France, 11, (44):53-63.
- Wassef, K., 1972. Study and comparison of automated versus conventional systems of modern spinning plant with special reference to the open-end spinning system. Hojas de Divulgacion. Asociacion de Investigacion Textile Algodonera, December:19-68.
- Yurkova, V. A., Moshkova, T. V., Altukhov, P. I., and Osipova, S. A., 1983. Yarn from BD-200-RS machines for knitted fabrics. Tekstill'naya Promyshlennost', 43, (5):47-48.
- Zellweger Uster Inc., December 1982. Uster Statistics, (31):34, 37.

APPENDIX: SLIVER EVENNESS (C.V.%)

Sliver Weight	Preparation	Cotton Fibers			
		Pima	California	W.T. Fine	W.T. Coarse
Coarse	Carded	5.54	5.58	5.65	6.73
	Combed	4.62	3.72	5.84	6.80
Fine	Carded	6.29	5.95	7.31	8.25
	Combed	5.98	5.06	8.23	7.71